

Mapefloor Parking System RLT

**MULTI-LAYERED, NON-SLIP EPOXY SYSTEM WITH 100% SOLIDS CONTENT
COMPLIANT WITH THE REQUIREMENTS OF CLASS OS 8 (EN 1504-2) FOR COATING
ROAD SURFACES IN CAR PARKS SUBJECTED TO LIGHT TO MEDIUM TRAFFIC.
TOTAL THICKNESS 0.8-1.2 mm**

Products used:

Primer SN - Mapefloor I 300 SL -

Mapecolor Paste - Quartz 0.5 - Quartz 0.25

DESCRIPTION

MAPEFLOOR PARKING

SYSTEM RLT is a multi-layered, seamless epoxy surface-coating system compliant with the requirements of Class OS 8 (EN 1504-2). It is suitable for moving vehicles, has a non-slip finish and is resistant to light to medium traffic in areas used for car parks.

MAPEFLOOR PARKING

SYSTEM RLT is characterised by its excellent resistance to wear and mechanical stress in general and high resistance to chemical products such as oil, fuel, de-icing salts, lubricants, diluted acids and base solutions and saline solutions in general.

Different colour finishes may be obtained which makes it extremely versatile for marking out areas according to their different use, such as parking areas, transit lanes, pedestrian areas, road signs and markings, etc.

WHERE TO USE

Coating for concrete floors and cementitious substrates subjected to light to medium volumes of traffic, such as road surfaces in covered car parks, multi-storey car parks, garages, etc.

MAPEFLOOR PARKING

SYSTEM RLT is used for the following:

- multi-storey car parks subjected to light to medium traffic;
- garages, transit areas for garages, etc.

PERFORMANCE AND ADVANTAGES

- Non-slip finish.
- Solvent-free, therefore safe for the environment.
- Resistant to most chemical products, such as diluted acids, base products, oil and fuel.
- Easy maintenance.
- Forms attractive, flat, seamless, highly functional surfaces.
- Reduces the time required to carry out work so lower down times of car parks.
- Excellent cost-performance ratio.

CHEMICAL RESISTANCE

Surfaces coated with **MAPEFLOOR PARKING SYSTEM RLT** are resistant to:

- diluted inorganic acids such as hydrochloric acid, nitric acid, phosphoric acid and sulphuric acid,


as well as limited resistance to organic acids;

- alkalis, including 50% sodium hydroxide solution and detergents normally used for cleaning floors up to a concentration of 20-30%, as long as they do not contain abrasive particles;
- mineral oils, diesel, kerosene and petrol;
- saline solutions in general, including those containing de-icing salts.

COLOURS AVAILABLE

MAPEFLOOR PARKING

SYSTEM RLT is available in the standard RAL colours 1001, 1013, 1015, 6021, 7001, 7030, 7032, 7034, 7035, 7037, 7040, 3009, 3016, 5007, 5012, 5024, 6001, 6017 and 6019. Requests for other colours not included in this list must be made to MAPEI Technical Services Department.



Mapefloor Parking System RLT

YIELD

The consumption levels indicated below are for a cycle applied at a temperature of between +15°C and +25°C and 80% maximum R.H. on the surface of a smooth, dry, compact, cured concrete screed with no rising damp strong enough to withstand the loads to which it will be subjected when in service, with a quartz sand finish polished with a diamond disk or lightly shot-blasted. Rougher surfaces and lower temperatures lead to higher consumption of the products, longer hardening times and longer delays before being put into service.

The consumption of **PRIMER SN** in particular may vary, depending on the type and depth of the treatment method used prepare the substrate.

MAPEFLOOR PARKING SYSTEM RLT - average thickness 0.8-1.2 mm

1° layer:

PRIMER SN

(A+B) +20%*

QUARTZ 0.5: 0.3-0.7 kg/m²

broadcast with

QUARTZ 0.5**

while still wet: 1.0-3.0 kg/m²

* The amount of **QUARTZ 0.5** filler required may vary, depending on the roughness and porosity of the substrate.

** To get a more pronounced non-slip finish, on access ramps for example, coarser quartz sand may be used, such as 0.3-0.9 mm or 0.7-1.2 mm.

Finishing coat:

MAPEFLOOR I 300 SL

(A+B +

MAPECOLOR PASTE)

+ **QUARTZ 0.25:** 0.64 kg/m²*

* The actual consumption level depends on the particle size of the sand used to dust the surface. A larger particle size will lead to a higher consumption rate.

N.B.: if coloured **MAPEFLOOR I 300 SL** is available, **MAPECOLOR PASTE** is not required.

This system must be strictly adhered to. Consumption of the products and materials is heavily influenced by the absorption, roughness and porosity of the substrate and the surrounding conditions on site during application.

TECHNICAL DATA (after 7 days at +23°C)

Adhesion (EN 13892-8)	>1.5 Nmm ²
BCA wear resistance (EN 13892-4)	AR 0.5
Impact strength (EN ISO 6272-1)	20 Nm
Capillary absorption and permeability to water (EN 1062-3)	w < 0.1 kg/m ² ·h ^{0.5}
Permeability to CO ₂ (EN 1062-6)	s _D > 50 m
Permeability to water vapour (EN ISO 7783)	Class III: s _D > 50 m
Reaction to fire (EN 13501-1)	B _(f1) -s1

SURFACE PREPARATION

1. Characteristics of the substrate

Before applying the **MAPEFLOOR PARKING SYSTEM RLT** cycle, the substrate on which the coating is to be applied must be carefully checked.

The concrete screed of the substrate must be sound, compact, strong and clean and must be dimensioned according to the static and dynamic loads to which it will be subjected when in service. The flatness must be defined according to the final use.

- To get the best results make sure the substrate has been sufficiently saturated, smoothed over and levelled off with **PRIMER SN**.
- There must be no materials or debris on the substrate which could potentially impede adhesion of the coating, such as:
 - cement laitance;
 - dust or detached or loose portions;
 - protective wax, curing products, paraffin or efflorescence;
 - oil stains or layers of dirty resin;
 - traces of paint or chemical products.

Any other kind of pollutant which may compromise adhesion of the coating must be removed before starting work. If the substrate is polluted by such elements, it **MUST** be prepared by carrying out a specific preparation cycle. If required, contact Mapei Technical Services Department for advice on the most suitable preparation cycle.

- The pull-off strength of the substrate must be higher than 1.5 N/mm².
- The level of humidity in the substrate must be a maximum of 4% and a

vapour barrier must be installed. For floors that have just been installed, wait until the concrete is fully cured before applying the resin system. If the residual moisture content is higher than 4%, apply **TRIBLOCK TMB** before the **MAPEFLOOR PARKING SYSTEM RLT** coating cycle to prevent detachment and/or the formation of blisters. If the floor is against a facing wall with rising damp, use a resin system permeable to water vapour.

- If all the above conditions are met, the system may be applied on concrete industrial floors, conventional or polymer-modified cementitious screeds, controlled-shrinkage screeds such as those made using **MAPECEM** or **TOPCEM** and old cement blocks and ceramic tiles, if prepared according to specification.

2. Preparation of the substrate

It is very important that the surface is prepared according to specification to guarantee correct application of the system and achieve the best performance levels.

The most suitable method to prepare the surface is shot-blasting, or alternatively grinding with a diamond disk. All dust must then be removed with a vacuum cleaner. Do not use chemical preparation methods, such as acid rinsing, or aggressive percussion tools, to prevent damaging the substrate. Any defects present on the surface, such as holes, pitting, cracking, etc., must be repaired beforehand using either **EPORIP** or

PRIMER SN, depending on the width and depth of the defects and cracks. If the substrate needs to be consolidated, use **PRIMER MF** or **PRIMER EP** (choose the most suitable product according to the porosity of the substrate, which will also have an effect on the consumption rate). If deep hollows or highly deteriorated areas are present on the surface of the floor, repair these areas using **MAPEFLOOR EP19** three-component epoxy mortar or with products from the **MAPEGROUT** range.

Highly deteriorated joints must be reconstructed using the same products.

If any of the above conditions are not strictly adhered to, the quality of the coating may be poor.

3. Preliminary checks before application

Make sure that all the checks from point 1 "Characteristics of the substrate" have been made and that all the operations indicated in point 2 "Preparation of the substrate" have been carried out correctly. The surrounding temperature must be higher than +8°C (the ideal application temperature is between +15°C and +25°C) and the temperature of the substrate must be at least 3°C higher than the dew-point temperature. Relative humidity of the surrounding air must be no higher than 80%.

4. Preparation and application of the products

Carefully follow the preparation instructions according to the Technical Data Sheet for each single product used to form the complete system:

PRIMER SN and **MAPEFLOOR I 300 SL**.

Non-slip multi-layered coating - 0.8-1.2 mm

• Primer (**PRIMER SN**)

Pour component B (4 kg) into component A (16 kg), add **MAPECOLOR PASTE** and mix with

a drill at low speed (300-400 rpm) with a spiral mixing attachment for at least 2 minutes to form a smooth, even compound. Whilst mixing, add 20% in weight of **QUARTZ 0.5** to the compound as soon as it has been prepared and mix again for several minutes to form a smooth, even compound. Pour the product onto the floor to be coated and spread it out evenly and uniformly by means of a straight trowel or range. After that, broadcast in excess with **QUARTZ 0.5**. Coarser sand may be used, such as 0.3-0.9 mm or 0.7-1.2 mm.

• Removal of excess sand

Once the **PRIMER SN** has hardened remove all excess sand with an industrial vacuum cleaner.

• Finishing layer

(**MAPEFLOOR I 300 SL**)

Pour component A (2 kg) into component B (6 kg) and mix with a drill at low-speed (300-400 rpm) with a spiral mixing attachment for at least 2 minutes to form a smooth, even compound. While mixing, add 0.5 kg of **QUARTZ 0.25** and 0.7 kg of **MAPECOLOR PASTE** to the compound as soon as it has been prepared and continue mixing to form a smooth, even compound. Apply the product uniformly and continuously and smooth it over the surface with a smooth rake, then pass over the surface with a medium-haired roller, making sure that the roll strokes criss-cross over each other.

Expansion joints and contraction joints in the flooring must be sealed with **MAPEFLEX PU 45**.

5. Hardening and step-on times

At +20°C **MAPEFLOOR PARKING SYSTEM RLT** sets to foot traffic after around 24 hours, while it takes 3 days before light traffic may use the surface. Complete hardening and maximum strength are reached after around

one week. Lower temperatures lead to longer hardening times and set to foot traffic times for the coating, while higher temperatures reduce these times.

6. Please note

Protect **MAPEFLOOR SYSTEM RLT** from water and condensation for at least 24 hours after application.

If the coating is exposed to aggressive chemicals it may yellow or the colour may change slightly. This phenomenon is purely aesthetic and has no effect on the performance of the system.

Do not apply the system if there is a high level of humidity.

CLEANING AND MAINTENANCE

Regular cleaning and maintenance increases the life of the treated floor, improves its aesthetic properties and reduces its tendency to collect dirt. Floors created using **MAPEFLOOR PARKING SYSTEM RLT** are generally easy to clean with neutral detergents, or with alkali detergents diluted at a concentration of from 5 to 10% in water. **MAPEFLOOR MAINTENANCE KIT** is available for maintenance operations, and includes **MAPELUX LUCIDA** metallic wax, **MAPEFLOOR WAX REMOVER** and **MAPEFLOOR CLEANER ED** detergent for daily cleaning operations. Our Technical Services Department is available for any information required.

NOTES

Recommendations regarding safe handling of the products are contained in the Material Safety Data Sheet for each single product in the cycle. However, the use of protective gloves and goggles is recommended when mixing and applying the products.

If the cycle is applied on surfaces, in climatic conditions and/or for final uses not mentioned above, please contact the Technical Services Department at MAPEI S.p.A.

